



VersaFlex Incorporated
 686 S. Adams Street
 Kansas City, KS 66105
 913-321-9000
 913-321-1490 (Fax)

Product Data Sheet

SL/60™ Joint Sealant

USGBC LEED, EQ Credit 4:
 Low-emitting VOC Compliant Materials

Product Description- *VersaFlex SL/60* is a self-leveling, 100% solids, flexible, two-component, rapid curing polyurea elastomer joint sealant material. **SL/60** is designed for 25% movement of an installed joint width. Recommended concrete cure of 30 days prior to installing joint filler or joint sealant.

Uses- *VersaFlex SL/60* is used to fill random cracks, contraction joints, control joints or new construction joints on new or old horizontal concrete surfaces. **SL/60** is ideal for use on elevated parking decks, balcony decks, pedestrian decks, bridge decks and on-grade slabs where its quick and positive cure will allow rapid turn around and return to use. **SL/60** is highly flexible, retaining full properties and memory capability while allowing normal joint movement and accommodating to slab movement where designed movement and thermal cycling will occur.

Ideal for Applications in:

- Parking decks
- Bridge decks
- Roofing
- Sidewalks
- Balcony decks
- Industrial facilities
- Water & waste water treatment

Advantages:

- 100% solids, no VOC's
- Exceptional elongation
- Remains flexible in cold temperatures
- Return project to service in 2 hours
- Cures from -20°F to 130°F
- Odorless, no toxic vapors
- Resists jet fuel
- USDA/FSIS/CSA approved

Joint Design- Joints receiving **SL/60** should be designed and prepared according to industry standards. In order to achieve optimum sealant movement characteristics, sealant depth should be ½ the sealant width, but in no case make the depth greater than 1" in any joint configuration.

Physical Properties-

(Typical) 1:1 Mix Ratio		
Cured Film Properties	Test Method	Typical Value
VOC	ASTM D3960	Zero
Solids content		100%
Pot life		0 minutes
Tack free		4 – 5 minutes
Initial cure		60 minutes
Final cure		7 days
The following properties are typical after maintaining cured product at 70°F - 77°F for seven days:		
Tensile strength (psi)	ASTM D412	460
Tensile elongation (%)	ASTM D412	650+%
Elastic modulus-100%, psi	ASTM D412	165
-300%, psi	ASTM D412	320
Tear strength (lb/in)	ASTM D624	130
Shore A hardness	ASTM D2240	60
Tabor abrasion, mg wt loss (1000 g, 1000 revs, H-18)	ASTM D4060	860
The value ranges stated in this Technical Data Sheet are based on system processing under laboratory conditions. Equipment configurations and/or field application conditions may produce variances in final system values.		

Limitations- **SL/60** should not be used on slopes greater than 15%. Backer rod (open cell) should be used in all joints with the exception of small random cracks.

SL/60 is an aromatic based polyurea. Discoloration from exposure to ultraviolet light may occur, however the physical properties are unaffected.

Coverage Rates-

Linear feet per gallon: Theoretical

Inches	1/4	1/2	3/4	1
1/4	308	154	103	72
1/2	154	77	51	38
3/4	103	51	34	26
1	72	38	26	19

Linear feet per 600ml cartridge: Theoretical

Inches	1/4	1/2	3/4	1
1/4	53	27	18	13
1/2	27	13	9	7
3/4	18	9	6	4
1	13	7	4	3

Packaging-

- One Hundred Ten Gallon Kit: 55 gallons of 'A' side and 55 gallons of 'B' side. Drum containers filled by weight, volume is closely approximated.
- Ten Gallon Kit: 5 gallons of 'A' side and 5 gallons of 'B' side
- Six Hundred ML Cartridges: 300ml of 'A' side and 300ml of 'B' side packaged as a duplex cartridge. Ten cartridges per case.

Mixing- Machine dispensing: Use 1:1 ratio pump with or without heater as required for individual application.

Colors- Standard color is light gray. Other colors available upon request. Consult ColorFlex chart at versaflex.com.

Preparation & Installation- Regard **VersaFlex** specification: Polyurea Joint Sealant for detailed joint preparation and installation procedures.

Clean Up- Cured product may be disposed of without restriction. Excess liquid 'A' & 'B' material should be mixed together and allowed to cure, then disposed of in the normal manner. Product containers that are "drip free" may be disposed of according to local, state and federal laws.

Safety- Review MSDS at VersaFlex.com

Basic safety for personal protection is:

- Long sleeve overalls or disposable Tyvex overalls
- Rubber gloves
- Splash shield or safety glasses with splash guards
- Rubber or leather boots
- Respirator
- Do not use near high heat or open flame
- Do not take internally
- Keep out of reach of children

Shelf Life- One year from date of shipment, in original, unopened factory containers, under normal storage conditions of 55°F to 95°F (18°-35°C).

Technical Services- Sales and Customer Support 913-321-9000

Warranty- **VersaFlex Incorporated** will refund the price of or replace, at its election, product it finds to be defective provided the product has been used properly. Except as expressly stated above, the company makes no warranty of merchantability and no warranty of fitness for any particular purpose, nor does it make any warranty, expressed or implied, of any nature whatsoever with respect to the product of its use. In no event shall the company be liable for delay caused by defects, for loss of use, for indirect, special or consequential damages, or for any changes or expenses of any nature incurred without its written consent.